## INDEPENDENT ASSURANCE LIMITED OBSERVATION CHECKLIST

Na			
Qualification # Date _		Date	_
	UMP OF HYDRAULIC CEMENT CONCRETE P FOR AASHTO T 119		
Tes	st Performed According to Procedure?	Yes N	No
1.	Cone and floor or base plate dampened?		
2.	Cone held firmly against the base by standing on the two foot pieces? Cone not allowed to move in any way during filling?		
3.	Representative samples scooped into the cone?		
4.	Cone filled in three approximately equal layers (by volume), the first to a depth of 67 mm (2 5/8 in), the second to a depth of 155 mm (6 1/8 in), and the third to just over the top of the cone?		
5.	Each layer rodded throughout its depth 25 times with hemispherical end of rod, uniformly distributing strokes?		
6.	Middle and top layers rodded to just penetrate into the underlying layer?		
7.	When rodding the top layer, excess concrete kept above the mold at all times?		
8.	Concrete struck off level with top of cone using tamping rod?		
9.	Concrete removed from around the outside bottom of the cone?		
10.	Cone lifted upward 300 mm (12 in) in one smooth motion, without twisting the cone, in $5 \pm 2$ seconds?		
11.	Slump measured to the nearest 5 mm $(1/4 \text{ in})$ from the top of the cone to the displaced original center of the top surface of the specimen?	<u> </u>	
12.	Test performed from start of filling through removal of the mold within 2 1/2 minutes?		
If'	No" was discrepancy corrected?  Date of "Split Sample"	Yes	No
	Signature of Examiner		

This checklist is derived, in part, from copyrighted material printed in ACI CP-1, published by the American Concrete Institute.

Part 8 - Materials Manual	<b>July 2005</b>
Independent Assurance	

## INDEPENDENT ASSURANCE LIMITED OBSERVATION CHECKLIST

	me					
Qualification # Date		te				
	AIR CONTENT OF FRESHLY MIXED CONCRETE BY THE PRESSURE METHOD FOP FOR AASHTO T 152					
Te	sts Performed According to Procedure?	Yes	No			
1.	Representative sample selected?					
2.	Dampened container filled in three equal layers, slightly overfilling the last layer?					
3.	Each layer rodded throughout its depth 25 times with hemispherical end of rod, uniformly distributing strokes?					
4.	Bottom layer rodded throughout its depth, without forcibly striking the bottom of the container?					
5.	Middle and top layers rodded, each throughout their depths and penetrating 25 mm (1 in.) into the underlying layer?					
6.	Sides of the container tapped 10 to 15 times with the mallet after rodding each layer?					
7.	Concrete struck off level with top of container using the bar or strike-off plate and rim cleaned off?					
8.	Top flange of base cleaned?					
Us	ing a Type B Meter:					
9.	Both petcocks open?					
10.	Air valve closed between air chamber and the bowl?					
11.	Inside of cover cleaned and moistened before clamping to base?					
12.	Water injected through petcock until it flows out the other petcock?					
13.	Water injection into the petcock continued while jarring and or rocking the meter to insure all air is expelled?					
14.	Air pumped up to just past initial pressure line?		-			
15.	A few seconds allowed for the compressed air to stabilize?					
16.	Gauge adjusted to the initial pressure?					
17.	Both petcocks closed?					
	OVER					

<b>Tests Performed According to Procedure?</b>	Yes	No
18. Air valve opened between chamber and bowl?		
19. The outside of bowl tapped smartly with the mallet?		
20. Air percentage read after lightly tapping the gauge to stabilize the hand to the nearest 0.1%?		
21. Air valve closed and then petcocks opened to release pressure before removing the cover?		
22. Aggregate correction factor applied if required?		
23. Air content recorded to 0.1 percent?		
If "No" was discrepancy corrected?  Date of "Split Sample"	Yes	No
Signature of Examiner		_

This checklist is derived, in part, from copyrighted material printed in ACI CP-1, published by the American Concrete Institute.

## INDEPENDENT ASSURANCE LIMITED OBSERVATION CHECKLIST

1.0			
Name			
MAKING AND CURING CONCRETE TEST SPECIMENS IN THE FIELD FOP FOR AASHTO T 23			
sts Performed According to Procedure?	Yes	No	
Molds placed on a level, rigid, horizontal surface free of vibration?			
Representative sample selected?			
Making of specimens begun within 15 minutes of sampling?			
Concrete placed in the mold, moving a scoop or trowel around the perimeter of the mold to evenly distribute the concrete as discharged?		_	
Mold filled in equal layers, attempting to exactly fill the mold on the last layer?		. <u>—</u>	
Each layer rodded throughout its depth 25 times with hemispherical end of rod, uniformly distributing strokes?		<u> </u>	
Bottom layer rodded throughout its depth?			
Subsequent layer(s) rodded throughout depth penetrating 25 mm (1 in.) into the underlying layer?		. <u>-</u>	
Sides of the mold tapped 10-15 times after rodding each layer?			
a. with mallet for reusable steel molds			
b. with the open hand for flexible light-gauge molds			
Concrete struck off with tamping rod or, if necessary, finished with a trowel or float?		. <u>-</u>	
Specimens covered with non-absorptive, non-reactive cap or plate?			
"No" was discrepancy corrected?  Date of "Split Sample"	Yes	No	
Signature of Examiner		_	

This checklist is derived, in part, from copyrighted material printed in ACI CP-1, published by the American Concrete Institute.

Part 8 - Materials Manual	<b>July 2005</b>
Independent Assurance	